



**WATCO®**  
**ALL-IN-ONE LACQUER + COLOR**

**DESCRIPTION AND USES**

Watco® All In One Lacquer + Color provides beautiful even color in a high gloss lacquer finish. Easy to apply, Watco All In One Lacquer + Color dries to the touch in 1 hour, leaves no brush marks and will not yellow. The ultra-high gloss finish applies rich color and lacquer evenly across interior wood surfaces, providing a smooth surface and long-lasting protection against surface scratches. Watco All In One Lacquer + Color adheres to bare wood and previously painted surfaces, eliminating the need for sanding sealer or primer.

Low odor and soap and water clean-up, makes Watco All In One Lacquer + Color ideal for use on all interior projects including: furniture, cabinets, doors, and paneling. Best when used on stained or bare wood surfaces. Not Recommended For: Floors or exterior surfaces.

**PRODUCTS**

SKU	DESCRIPTION (Quart)
342785	Light Tint Base
342787	Dark Tint Base

**PRODUCT APPLICATION**

**SURFACE PREPARATION**

For best adhesion all surfaces must be clean, dry, and free of wax, grease, oil, shellac, mildew, and polishes. Remove wax with a wax stripper, shellac with a paint stripper, and mildew with a solution of 10% household bleach and water.

Old finishes in poor condition must be removed. Sand to obtain a smooth surface. Remove all sanding dust using a vacuum or cloth dampened with mineral spirits.

**WARNING:** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**PRODUCT APPLICATION (cont.)**

**THIS PRODUCT MUST BE TINTED AT PAINT COUNTER BEFORE USING.**

**APPLICATION**

Use adequate ventilation at all times. Do not apply in direct sunlight. Apply only when the air and surface temperatures are between 55-90°F (13-32°C) and the relative humidity is below 85%. Test in an inconspicuous area before beginning.

Stir thoroughly before and during use. To prevent bubbles in the finish, **DO NOT SHAKE**, over brush, or apply with a roller. Apply using a good quality synthetic bristle. Allow to dry 1 hour and then recoat. Recoat only when previous coats have dried and feel hard. 2 - 3 coats are recommended.

**DO NOT THIN**

**DRY & RECOAT**

Dry and recoat times are based on 77°F (25°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch and can be recoated in 1 hour. Allow to dry 24 - 48 hours prior to light use. Allow to cure 7 days before subjecting surface to normal usage.

**CLEAN UP**

Clean tools and equipment with soap and water.

	<b>TECHNICAL DATA</b>	<b>WAT-19</b>
<b>WATCO® ALL-IN-ONE LACQUER + COLOR</b>		

**PHYSICAL PROPERTIES**

		ALL-IN-ONE LACQUER +COLOR	
		LIGHT TINT BASE	DARK TINT BASE
<b>Resin Type</b>		Oil modified polyurethane	Oil modified polyurethane
<b>Pigment Type</b>		TiO <sub>2</sub>	None
<b>Weight</b>	<b>Per Gallon</b>	9.8 lbs.	8.7 lbs.
	<b>Per Liter</b>	1.2 kg	1.0 kg
<b>Solids</b>	<b>By Weight</b>	46%	35%
	<b>By Volume</b>	36%	30%
<b>Volatile Organic Compounds</b>		≤140 g/l	≤140 g/l
<b>Recommended Dry Film Thickness (DFT) per Coat</b>		1.5-2 mils	1.5-2 mils
<b>Wet Film to Achieve DFT (unthinned material)</b>		4-5 mils	5-7 mils
<b>Practical Coverage at Recommended DFT (assume 15% material loss)</b>		Up to 65 sq.ft./can	Up to 45 sq.ft./can
<b>Dry Times at 77°F (25°C) and 50% Relative Humidity</b>	<b>Touch</b>	1 hour	1 hour
	<b>Handle</b>	24 hours	48 hours
	<b>Recoat</b>	1 hour	1 hour
	<b>Full Cure</b>	7 days	7 days
<b>Flash Point</b>		>200°F (93°C)	>200°F (93°C)
<b>Shelf Life</b>		3 Years	
<b>Safety Information</b>		For additional information, see SDS	

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.