

• TRUSTED QUALITY SINCE 1921 •
RUST-OLEUM®
 SPECIALTY

RUST-OLEUM® SPECIALTY CEMENT PAINT

DESCRIPTION AND USES

Rust-Oleum® Specialty Cement Paint is an innovative paint that provides the natural look and feel of cement in an aerosol. Cement paint transforms any object to look as if it is made of cement. For use on interior surfaces only. Not intended for cement surfaces.

PRODUCT

SKU	DESCRIPTION (Aerosol)
323384	Cement Paint

PRODUCT APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 65% to ensure proper drying. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy or porous surfaces. Remove any wax by lightly wiping surface with mineral spirits and let dry.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Priming is not required for most surfaces. For superior coverage, a Rust-Oleum® primer can be used for surfaces such as bare wood and treated wood.

PRODUCT APPLICATION (cont.)

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle, DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. May recoat within 1 hour or after 48 hours. Dries to the touch in 30 minutes and to handle in 1 hour. Fully dry in 24 hours.

NOTE: On plastic, maximum paint adhesion and durability is achieved in 5-7 days.

CLEAN-UP

When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. Clean up wet paint with xylol or mineral spirits. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	TECHNICAL DATA	SPC-70
<small>• TRUSTED QUALITY SINCE 1921 •</small> RUST-OLEUM® SPECIALTY	RUST-OLEUM® SPECIALTY CEMENT PAINT	

PHYSICAL PROPERTIES

		CEMENT PAINT
Resin Type		Alkyd
Pigment Type		Titanium Dioxide, Aluminum
Solvents		Acetone, Naptha, Xylene
MIR		0.80 Max
Fill Weight		12 ounces
Dry Times at 77°F (25°C) and 50% Relative Humidity	Touch	30 minutes
	Recoat	Within 1 hour or after 48 hours
	Handle	2 hours
	Full Cure	7 days
Shelf Life		12 months
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.